

		Sprayed Thermoplastic
Material Application Temperature	Ambient °C	200°C +
Machine Preparation time	25 minutes	2 hours +
Fill up time	30 – 45 minutes	30 – 45 minutes
Application volume per tank of material	2,500m ² (25,000m x 100mm)	350m ² (3,500m x 100mm)
Application speed	10 - 12 km / hour	6 km / hour
Application thickness	0.35mm	1.5mm
Dry time to traffic	1 minute	1 minute
Mcd/m ² /lux on application	550	180
Mcd/m ² /lux after 24 months	200 +	80 - 100

www.QMSHyperLine.co.uk